



UV RESISTANCE
100% NYLON 6.6 SEWING THREAD

Duralon UV®

DURAK Duralon UV® is a high tenacity nylon 6.6 sewing thread with UV resistance. This feature protects the thread against the negative effects of UV lights such as discoloration, low abrasion resistance and loss of tenacity. All these negative effects are called UV destruction. Duralon UV® minimizes this destruction. It is an excellent sewing thread with high resistance against abrasion in high speed sewing. It has a soft structure which reduces the effects of needle heat and provides excellent abrasion resistance.



Product Properties

- ✦ Minimizes UV destruction.
- ✦ High tenacity and sewing elasticity.
- ✦ Effect that prevents fading of colors.
- ✦ Provides superior sewing performance with its high-technology finishing processes and lubricants.

Duralon UV®

Areas of Use

- Outdoor Textiles
- Furniture
- Automotive
- Tent / Tarpaulin

Physical Properties

Melts at 260°C and softens at 190°C.

Shrinkage is less than 1% at 150°C.

Chemical Properties

Mineral acids: Soluble by strong mineral acids, resistant to weak acids.

Alkalis: Resistant to weak alkalis but it can be damaged by strong alkalis at high temperatures.

Organic solvents: Generally unaffected.

Bleaching: Unaffected.

Microorganisms (Mildew/Rot): Unaffected.

Moisture regain: %0.4



Presentation

Durak Duralon UV® offers a wide range of colors in a variety of meters size and thicknesses.

Color Fastness

Washing fastness at 60°C	ISO 105 C06	Min. 4
Water fastness	ISO 105 E01	Min. 4
Friction fastness	ISO 105 X12	Min. 4
Hypochlorite fastness	ISO 105 N01	Min. 4
Dry cleaning fastness	ISO 105 D01	Min. 4
Perspiration fastness	ISO 105 E04	Min. 4
Artificial light fastness	ISO 105 B02	Min. 4

Storage Conditions

Must be stored away from heat, humidity and direct sunlight.





Duralon UV®

Thickness and Strength Chart

Ticket No.	Nominal Tex	Strength CN	Elongation %	Needle Size (Nm)
8	400	30.000	45 - 55	160 - 200
10	250	19.000	22 - 32	160 - 200
15	180	14.500	22 - 32	120 - 160
20	150	10.250	22 - 32	120 - 140
30	105	6.630	22 - 32	110 - 130
40	70	5.000	18 - 28	100 - 120
60	45	3.420	18 - 28	90 - 100
80	35	2.500	12 - 25	75 - 90

Other Duralon Sub-Brands

- Duralon WR®** 100% high tenacity nylon 6.6 sewing thread with water repellent. It has a PCF-free water repellent surface coating.
- Duralon AS®** Antistatic sewing thread made of 100% high tenacity nylon 6.6, pre-stabilized together with a conductive material. It is designed for use in applications where electrostatic charge is a problem.
- Duralon OS®** 100% high-tenacity nylon 6.6 sewing thread with special finishing processes in order to provide high sewing performance in the most challenging conditions. A controlled lubrication process is applied by excluding substances such as silicone, grease, graphite, wax and paraffin during the finishing process.
- Duralon CFR®** 100% high tenacity nylon 6.6 sewing thread produced by adding flame-retardant characteristics. The thread surface is coated with flame retardant chemical in accordance with the standards of chemical coating method.